



**WAGENINGEN EVALUATING PROGRAMS
FOR ANALYTICAL LABORATORIES**

Certificate of Analysis



International Plant-Analytical Exchange

REFERENCE MATERIAL

IPE sample 240



General Information

In this report an overview is given of analytical data for this sample collected in our proficiency testing program. The consensus values are calculated using a robust statistical model. With this NDA model mean and standard deviation are calculated using all reported data when at least 8 results are left after removal of reported 'lower than' (<) and 0 (= zero) values. No outliers are removed.

This report is divided into three sections: Consensus Values, Indicative Values and Values for Information. The division is made on the reliability of the data. Consensus Values are based on at least 16 results while the coefficient of variation is smaller than 25 %. Indicative Values are based on at least 8 and less than 16 results or a coefficient of variation between 25 % and 50 %. Other values, based on more than 2 and less than 8 results or a coefficient of variation higher than 50 %, are given for information only.

In the sections with Consensus Values and Indicative Values the following parameters are given: mean, standard deviation, coefficient of variation, number of results, median and MAD (Median of Absolute Deviation) and the uncertainty in the consensus values. The confidence limits (at 95 % probability) are calculated for these determinands.

In the section with Information Values the following parameters are given: median, MAD and number of results. For determinands which have at least 5 results reported as smaller than (<) the median of these 'smaller than results' is calculated. In some cases this median of '<' values is much smaller than median and mean of the indicative values. This may be caused by a too optimistic (too low) value for the detection limit reported by a (small) majority of participating laboratories who report '<' -values.

All values, expressed on a weight basis (kg or %), are reported in oven dry (105 °C) material. Moisture is reported in the material as received.

Sample information

WEPAL reference materials are from natural sources only. There is no spiking, mixing or other alterations of the samples. For sample preparation the IPE samples are dried at 70 °C and milled to pass a 0.5 mm sieve.

This IPE sample 240 of Beech wood / *Fagus sylvatica* from Netherlands is prepared for the WEPAL proficiency programs. The sample is used in 1 period (or round). The results on which the values in this report are based were taken from the period given in the following table.

Year	Round	Number
2018	1	1



Consensus Values IPE 240



Method: Inorganic Chemical Composition

Element	Unit	Mean	Std.Dev.	CV %	N	Median	MAD	Uncertainty	95 % confidence limits		
Ba	mg/kg	35.0	2.09	6.0	18	34.8	1.50	0.62	34.0	-	36.1
Ca	g/kg	1.25	0.116	9.3	101	1.26	0.080	0.014	1.23	-	1.27
Cd	µg/kg	64.7	8.46	13.1	31	66.0	6.00	1.90	61.6	-	67.8
Co	µg/kg	41.2	2.02	4.9	17	41.5	1.50	0.61	40.2	-	42.2
K	g/kg	1.60	0.172	10.7	107	1.61	0.120	0.021	1.57	-	1.64
Mg	g/kg	0.313	0.0289	9.2	101	0.320	0.0200	0.0036	0.308	-	0.319
Mn	mg/kg	75.1	4.76	6.3	103	74.8	3.18	0.59	74.2	-	76.1
Ni	µg/kg	568	97.2	17.1	21	561	64.2	26.5	524	-	612
P (as P)	g/kg	0.0666	0.0158	23.7	93	0.0700	0.0110	0.0020	0.0634	-	0.0699

Method: Real totals

Element	Unit	Mean	Std.Dev.	CV %	N	Median	MAD	Uncertainty	95 % confidence limits		
C - elementary	g/kg	489	9.9	2.0	34	488	6.8	2.1	485.7	-	492.6



Indicative Values IPE 240



Method: Inorganic Chemical Composition

Element	Unit	Mean	Std.Dev.	CV %	N	Median	MAD	Uncertainty	95 % confidence limits		
B	mg/kg	2.67	0.879	33.0	74	2.85	0.624	0.128	2.46	-	2.87
Cu	mg/kg	1.09	0.326	29.9	88	1.10	0.230	0.044	1.02	-	1.16
Fe	mg/kg	7.19	3.156	43.9	89	8.00	2.276	0.418	6.53	-	7.86
N - Kjeldahl (as N)	g/kg	1.20	0.461	38.4	58	1.24	0.335	0.076	1.08	-	1.32
S (as S)	g/kg	0.0957	0.0245	25.6	52	0.1000	0.0180	0.0043	0.0889	-	0.103
Sr	mg/kg	6.91	0.387	5.6	14	6.86	0.290	0.129	6.68	-	7.13
Zn	mg/kg	3.36	1.245	37.0	95	3.48	0.875	0.160	3.11	-	3.62

Method: Real totals

Element	Unit	Mean	Std.Dev.	CV %	N	Median	MAD	Uncertainty	95 % confidence limits		
N - elementary	g/kg	1.24	0.399	32.2	46	1.28	0.271	0.074	1.12	-	1.36

Method: Nutritional values

Element	Unit	Mean	Std.Dev.	CV %	N	Median	MAD	Uncertainty	95 % confidence limits		
Total ash	g/kg	6.40	1.346	21.0	12	6.29	0.900	0.486	5.55	-	7.25



Informative Values IPE 240



Method: Inorganic Chemical Composition

Element	Unit	Median	MAD	N	Results smaller than (<)	
					Median of <	N
Ag	µg/kg	14.1	7.98	4		
As	µg/kg	13.3	6.90	11	100.0	17
Be	µg/kg	-	-	0	100	7
Cl (as Cl)	g/kg	0.270	0.2290	11	0.500	5
Cr	µg/kg	105	52.7	12	250	14
Hg	µg/kg	3.10	1.001	8	10.00	13
Li	µg/kg	26.1	12.55	6	308.5	6
Mo	µg/kg	120	110.0	15	200	25
N - NO3 (as N)	mg/kg	26.2	3.80	3		
Na	mg/kg	10.92	8.350	37	50.00	23
Pb	µg/kg	58.9	24.16	21	500.0	15
Rb	µg/kg	3080	99	5		
Sb	µg/kg	2.12	0.480	3	12.70	7
Se	µg/kg	13.6	9.59	5	61.7	16
Sn	µg/kg	45.3	41.90	3		
Ti	mg/kg	0.316	0.0705	4		
V	µg/kg	7.93	5.080	6	154.00	10

Method: Real totals

Element	Unit	Median	MAD	N
Al	mg/kg	4.60	1.495	4

Method: Acid extractable (So-called totals)

Element	Unit	Median	MAD	N	Results smaller than (<)	
					Median of <	N
Al	mg/kg	5.11	2.495	20	12.60	8

Method: Other determinations

Element	Unit	Median	MAD	N
delta 13C	‰ V-PDB	-25.9	0.04	5

Method: Nutritional values

Element	Unit	Median	MAD	N
ADF-ash-free	g/kg	737	13.8	3
Crude fibre	g/kg	673	16.0	7



Informative Values IPE 240

NDF-ash-free	g/kg	945	0.3	3
Total fat	g/kg	5.58	2.580	3